

**ARP PLASTER PRIMER****PRODUCT CODE: 176020 – LINE**

(Page 1 of 2)

**GENERAL DESCRIPTION:**

- Alkali resistant primer and sealer for use on alkaline surfaces such as asbestos cement and new plaster.
- Versatile combination of high solids with good sealing properties.
- Serves as primer and sealer with one application.
- Quick drying properties preventing dirt pick-up.

**USES:**

- Recommended primer and sealer for all new interior and exterior porous surfaces such as asbestos cement, plaster, brick, cement and various types of composition boarding.
- Suitable primer for penetrating and sealing porous alkaline surfaces when overcoating with Universal Undercoat and Enamel is required.
- Suitable primer for binding chalked but sound PVA or lime wash to the original surface when overcoating with subsequent coats of emulsion paint.

**TECHNICAL DATA:**

Type	-	Blend of Oleo-resinous, alkali resistant alkyd resin.
Drying Time	-	Surface: 1 hour (at 25°C and 50% relative humidity).
	-	Hard Dry: 14-16 hours (at 25°C and 50% relative humidity)
Recoating	-	16 hours (Overnight)
Viscosity	-	69 - 72 Ku's
Specific Gravity	-	1.47 - 1.49
Gloss	-	Semi-gloss
Weight solids	-	71-73%
Volume solids	-	52-54%
Spreading Rate	-	14-15m <sup>2</sup> / litre (to obtain a continuous film without full coverage)
Coverage (theoretical)	-	4-5m <sup>2</sup> / litre (to obtain 100% coverage with one application)
Flash Point	-	Over 21°C
Colour Range	-	Off-white
Packing Size	-	500ml, 1litre, 5 litre and 25 litre.

Coverage / spreading rate of ARP Plaster Primer depend on condition and porosity of the surface and the manner in which ARP Plaster Primer is applied and used. For best results, do not exceed a spreading rate of 8m<sup>2</sup> / litre.

**APPLICATION:**

- Ready for use with brush or roller.
- Brush application is preferred to ensure best penetration.
- Thinning
  - Not recommended.
- Equipment cleaning
  - Turps / White Spirits

## **ARP PLASTER PRIMER**

**PRODUCT CODE: 176020 – LINE**

(Page 2 of 2)

### **STANDARD APPLICATION PROCEDURE:**

- |   |   |  |
|---|---|--|
| New Surfaces :<br>Brick, Plaster, Cement<br>Asbestos Cement   | - | Remove dust, dirt and plaster splashes.<br>Cut out large cracks and imperfections.<br>Fill with Dekro Liquifill Crack Filler and sand smooth when dry. |
|   | - | Apply one coat of ARP Plaster Primer.  |
|   | - | Allow to dry minimum 16 hours (overnight) before overcoating.  |
|   | - | Overcoat with Universal Undercoat or emulsion paint depending on type of surface or quality of final finish required.                                  |
| Previously painted surfaces<br>Re-decoration: PVA<br>Emulsion, distemper<br>Lime-wash - in poor condition | - | Remove completely by scraping, wire brushing, hydro blasting to bare, sound surface.   |
|   | - | Stop and fill all cracks and imperfections with an appropriate crack filler. Allow to dry and sand smooth when dry.                                    |
|   | - | Apply one coat of ARP Plaster Primer.  |
|   | - | Allow to dry minimum 16 hours (overnight) before overcoating.  |
|   | - | Overcoat with Universal Undercoat or Emulsion paint depending on type of surface or quality of final finish required.                                  |

### **GENERAL:**

- Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
- It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

### **PRECAUTIONS:**

- ARP Plaster Primer will not penetrate a multiplicity of coats of powder and it is essential to prepare the surface prior to the application of ARP Plaster Primer.
- Do not apply to fresh uncured concrete.
- Do not apply to damp or wet surfaces.
- Not suitable as a primer for metal surfaces (hinges), use recommended primer for spot-priming metal surfaces.
- Clean all equipment and tools with Turps after use.

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the users responsibility to confirm the currency of product data sheets.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: [www.dekro.co.za](http://www.dekro.co.za) e-mail: [info@dekro.co.za](mailto:info@dekro.co.za)