

BITUMINOUS ALUMINIUM PAINT

PRODUCT CODE: 164001 – LINE

(Page 1 of 2)

GENERAL DESCRIPTION:

- High lustre Bituminous Aluminium paint.
- Free from bleeding on bituminous surfaces.
- Improves illumination and reflects heat.

USES:

- Direct application to bituminous surfaces, “Malthoid” roofs and creosoted timber.

TECHNICAL DATA:

Type	-	Blend of bituminous surfaces resins, pigmented with leafing aluminium.
Drying Time	-	Surface: 2 - 3 hours (at 25 ⁰ C and 50% relative humidity). Hard Dry: 6 - 8 hours (at 25 ⁰ C and 50% relative humidity)
Recoating	-	8 hours
Viscosity	-	32 - 35 Sec. Ford 4 cup
Specific Gravity	-	0.98 - .099
Gloss	-	High Lustre
Weight solids	-	56 - 57%
Volume solids	-	46 - 47% (100μ wet film will give 47μ dry film)
Spreading Rate	-	35 - 38m ² / litre (to obtain a continuous film without full coverage)
Coverage (theoretical)	-	12 - 15m ² / litre (to obtain 100% coverage with one application)
Flash Point	-	Over 21°C
Colour	-	Aluminium
Packing Size	-	1 litre, 5 litre, 25 litre.

APPLICATION:

- Ready for use with brush or roller.
- For spray application thin with Mineral Turps only.
- Thinning - Not recommended, except for application by spray.
- Equipment Cleaning - Mineral Turps.

STANDARD APPLICATION PROCEDURE:

- Does not require elaborate surface preparation except that surfaces must be clean and dry before application.
- For very absorbent surfaces such as asbestos cement, apply one initial sealing coat of Dekro Bituminous Black Paint.
- For new work, apply two coats. Allow to dry between coats.
- For general maintenance apply one coat.

BITUMINOUS ALUMINIUM PAINT

PRODUCT CODE: 164001 – LINE

(Page 2 of 2)

GENERAL

- Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
- It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

PRECAUTIONS

- Not to be used over very soft bitumen and pitch where the difference in elasticity of the two systems will lead to “crocodiling”.
- Not suitable as heat resistant paint.

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the users responsibility to confirm the currency of product data sheets.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za e-mail: info@dekro.co.za