

BITUMINOUS PAINT

BLACK

PRODUCT CODE: 164003

(Page 1 of 2)

GENERAL DESCRIPTION

- General purpose protective coating
- Impervious to moisture and most chemicals.
- Low cost, high solid content.
- Acceptable glossy appearance.

USES

- Recommended for sealing absorbent surfaces such as asbestos cement prior to the application of a finishing coat Of Bituminous Aluminium.
- Direct application to any clean metal surfaces where a low cost protective coating is required.

TECHNICAL DATA

Type	:	Blend of Bituminous Resins with inorganic fillers.
Drying time	:	Surface : 2 – 4 hours (at 25°C and 50% relative humidity). Hard dry : 6 – 8 hours (at 25°C and 50% relative humidity).
Re-coating	:	24 hours
Viscosity	:	125 - 130Ku's
Specific gravity	:	1,02 – 1,03
Gloss	:	Glossy
Weight solids	:	79 - 80%
Volume solids	:	73 – 74% (100µ wet film will give 74µ dry film)
Spreading rate	:	15 - 17 m ² /litre (to obtain a continuous film without full coverage)
Coverage (theoretical)	:	8 - 10m ² /litre (to obtain a 100% coverage with one application).
Flash point	:	Over 21°C
Colour range	:	Black only
Packing size	:	5 litre

Coverage / spreading rate of Dekro Bituminous Black depends on the condition and porosity of the surface and the manner in which it is applied and used.

APPLICATION

- Ready for use with brush or roller.
- For spray application thin with Spraying Enamel Thinners.
- Thinning - Not recommended, except for application by spray.
- Clean equipment with Mineral Turps or Spraying Enamel Thinners.

BITUMINOUS PAINT

BLACK

PRODUCT CODE: 164003

(Page 2 of 2)

STANDARD APPLICATION PROCEDURE

- Does not require elaborate surface preparation, except that surfaces must be clean and dry before application.
- For new metal work apply two to three coats, depending on the severity of the conditions.
- When recoating, do not work the brush or roller too much over the same area, as this product is easily re-dissolved.
- To seal absorbent surfaces apply one coat.
- For general maintenance apply one coat.

GENERAL

- Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
- It is therefore recommended that you contact a Dekro Sales Representative for advice on all your painting requirements whenever possible.

PRECAUTIONS

- Do not overcoat with decorative top coats as bleeding will occur.
- All solvents will soften the film.
- Should not be exposed to direct sunlight as this can cause premature breakdown of the film.
- Dry Dekro Bituminous Black paint can be removed with Mineral Turps.

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za e-mail: info@dekro.co.za