

STANDARD ALUMINIUM PAINT

PRODUCT CODE: 166080 – LINE

(Page 1 of 2)

GENERAL DESCRIPTION

- Ready mixed leafing aluminium paint.
- General purpose high lustre aluminium.
- Protective coating for iron, steel, wood and other surfaces.
- Improves illumination.
- Reflects heat

USES

- For all interior and exterior suitable primed surfaces of metal and wood where an aluminium finish is required.
- This includes hot areas below 90°C.

TECHNICAL DATA

Type	-	Blend of long oil alkyd, hydrocarbon resin.
Drying Time	-	Surface: 2 - 3 hours (at 25 ⁰ C and 50% relative humidity).
	-	Hard Dry: 6 - 8 hours (at 25 ⁰ C and 50% relative humidity).
Recoating	-	8 hours
Viscosity	-	32 - 35 Sec. Ford 4 cup.
Specific Gravity	-	0.94 - 0.95
Gloss	-	Sheen
Weight solids	-	55 - 56%
Volume solids	-	44 - 45% (100µ wet film will give 44µ dry film)
Spreading Rate	-	28 - 30m ² / litre (to obtain a continuous film without full coverage)
Coverage (theoretical)	-	17 - 19m ² / litre (to obtain 100% coverage with one application)
Flash Point	-	Over 21°C
Colour Range	-	Aluminium
Packing Size	-	500ml, 1 litre, 5 litre, 25 litre.

All above technical data of coverage / spreading rate depend on condition and porosity of the surface and the manner in which Dekro Standard Aluminium paint is applied and used.

APPLICATION

- Ready for use with brush or roller.
- For spray application thin with Mineral Turps only.
- Brush application is preferred.
- Roller application tends to give too low film thickness and a “window pane” effect.
- Thinning - Not recommended, except for application by spray.
- Equipment Cleaning - Mineral Turps

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za e-mail: info@dekro.co.za

STANDARD ALUMINIUM PAINT

PRODUCT CODE: 166080 – LINE

(Page 2 of 2)

STANDARD APPLICATION PROCEDURE

- Surfaces must be clean and dry before application.
- Steel, wood and galvanised iron surfaces must be suitably primed prior to the application of Dekro Standard Aluminium paint.
- For new work apply two coats.
- Allow at least 8 hours (overnight) drying time between coats.
- for general maintenance apply one coat or touch up bare areas.

GENERAL

- Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
- It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

PRECAUTIONS

- Not suitable for direct application to bare metal.
- Not suitable as roof paint.
- Not suitable for painting surfaces which exceed 90°C temperature.

Technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the users responsibility to confirm the currency of product data sheets.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za e-mail: info@dekro.co.za