

TENNIS COURT PAINT

PRODUCT CODE: 110 040

(Page 1 of 2)

GENERAL DESCRIPTION :

- High quality tennis court paint.
- Dries to a smooth matt finish.
- Excellent application with brush or roller.

TECHNICAL DATA :

Type	-	Acrylic, Co-polymer Emulsion.
Drying Time	-	Surface : ½ - 1 hour (at 25°C and 50% relative humidity) Hard Dry : 3 - 4 hours (at 25°C and 50% relative humidity)
Re-coating	-	4 hours.
Viscosity	-	98 - 100 KU
Specific gravity	-	1,2 – 1,3
Gloss	-	Matt finish (20° - 1% / 60° - 6% / 85° - 14%)
Weight solids	-	40 – 43%
Volume solids	-	26 – 29%
Spreading rate	-	11 - 12m ² (to obtain a continuous film without full coverage).
Coverage (theoretical)	-	5 - 6 m ² (to obtain 100% coverage with one application).
Flash point	-	Not applicable.
Colour	-	Tennis Court Green.
Packing size	-	5 litre and 20 litre.

STANDARD APPLICATION PROCEDURE :

New Surfaces :	-	Remove dust, dirt and plaster splashes. Cut out large cracks and imperfections. Fill with Profill and sand smooth when dry.
	-	Apply one coat of Dekrolite Masonry Paint to new surfaces.
	-	Allow to dry.
	-	Apply two coats of Tennis Court paint.
	-	Allow at least 4 hours drying time between coats.
Previously coated surfaces	-	Remove loose paint completely by scraping or wire brushing.
	-	Fill all large cracks and imperfections and Profill. Allow to dry and sand smooth when dry.
	-	Ensure surface is sound, clean and dry.
	-	Apply one coat of Dekrolite Masonry Paint or Dekroseal Pigmented Emulsion Primer, allow to dry.
	-	Apply two coats of Tennis Court paint.
	-	Allow at least 4 hours drying time between coats.
Previously coated surfaces	-	Remove loose paint completely by scraping or wire brushing.
	-	Fill all large cracks and imperfections and Profill. Allow to dry and sand smooth when dry.
	-	Ensure surface is sound, clean and dry.
	-	Apply one coat of Dekrolite Masonry Paint or Dekroseal Pigmented Emulsion Primer, allow to dry.
	-	Apply two coats of Tennis Court paint.
	-	Allow at least 4 hours drying time between coats.

TENNIS COURT PAINT

PRODUCT CODE: 110 040

(Page 2 of 2)

GENERAL

- Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
- It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage or whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the users responsibility to confirm the currency of product data sheets.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za e-mail: info@dekro.co.za