

HYDROLOCK PRIMER

CODE: 309001

REVISION : 02

DATE: 06 August 2024

GENERAL DESCRIPTION

Water based 2-component epoxy for use on most sound and eroded building substrates where a bonding effect is required.

USES AND PROPERTIES

Hydrolock Primer is a rapid curing, water based primer consisting of two components; a pre-reacted epoxy resin dispersed in water (Part A), and a waterborne modified polyamine solution (Part B). In its wet mixed state, it is off white and dries to a clear finish.

Hydrolock Primer is suitable for use on most sound and eroded building surfaces where both a penetrative and bonding effect is needed. Substrates include concrete (including damp and partially cured cementitious renders, screeds and mortars, bituminous surfaces (e.g. asphalt), roofing felts, insulation foams, wooden protrusions, previously painted surfaces, glass reinforced polyester and waterproofing membranes prior to re-coating. The product's rapid curing properties allow faster contract completion and consequent savings on site/labour costs.

TECHNICAL DATA

Binder Type	:	Water based 2-component epoxy
Drying Time	Surface	: <2 hours (at 23°C and 50% humidity)
	Hard	: <4 hours (at 23°C and 50% humidity)
Drying Process	:	Water evaporation followed by crosslinking
Overcoating	Water based	: 2 hours (maximum 24 hours)
	Solvent based	: 4 hours (maximum 5 days)
Viscosity	:	85 - 90KU
Specific Gravity	:	1,03 ±0,025kg/litre
Mass Non-Volatile Content	:	18% ±3%
Volume Solids	:	16% ±3%
Coverage	:	10m ² /litre
Dry Film Thickness	:	16 microns @ 10m ² /litre
Colour Range	:	Off white
Mix Ratio	:	4 :1 (A : B) by weight and volume
Clean Equipment With	:	Water
Pack Sizes	:	1 litre, 5 litre

Coverage/spreading rate of **Hydrolock Primer** depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

HYDROLOCK PRIMER

APPLICATION

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications. Copies of these are available on request from Dekro Paints or can be downloaded from our website –www.dekro.co.za.

Do not apply when ambient temperatures are $<4^{\circ}\text{C}$ or $>40^{\circ}\text{C}$.

After correct surface preparation, prime **Hydrolock Primer** by brush, roller or spray at the specified spread rate as per technical data.

SAFETY INSTRUCTIONS

Always keep out of reach of children and animals.

Wear a suitable dust mask and goggles when preparing surfaces.

Ensure good ventilation during application and drying.

If accidental contact with skin, wash immediately with soap and water or a recognised skin cleaner.

If accidental contact with eyes, rinse immediately with plenty of water and seek medical advice.

Harmful if swallowed. Seek medical attention and do not induce vomiting.

GENERAL

Different surfaces and environmental conditions require specific painting systems to produce the best possible results.

It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

PREVENTING PROBLEMS AND GENERAL INFORMATION

IMPORTANT: Walls (cement plaster, concrete or masonry) must be dry before painting and should not exceed a moisture content of 10% as measured with a Protimeter Surveymaster Moisture Meter or equal. The ambient temperature must be between 4°C and 40°C and humidity between 10% and 85%.

Excessive application thickness and/or rapid drying could lead to mud cracking.

Avoid applying under adverse weather conditions as this could result in poor product performance.

Work from corner to corner, or from a natural cut off point to another.

Do not attempt touch ups, but redo complete panels.

Always keep a wet edge and avoid downing tools during the application process to prevent lap marks and variances in colour or texture.

To ensure consistent appearance ensure that the batch numbers on all containers used are the same. Where batch numbers on containers differ, intermix containers before use.

HYDROLOCK PRIMER

CLEANING, STORAGE AND DISPOSAL

Remove as much paint as possible from application equipment and wash immediately after use with water. Close containers tightly after use and store in a cool well-ventilated area. Do not empty contents or wash water into drains or water courses. When disposing please follow local authorities' regulations and recycle the container after use.

Technical Data Sheet



DEKRO
IS THE ARCHITECTS CHOICE

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.