

FLEXI COAT

Page 1 of 2

CODE: 654001

REVISION: 02

DATE: 09 December 2025

GENERAL DESCRIPTION

Flexi Coat is an Acrylic based coating that has a low sheen finish.

USES AND PROPERTIES

This product can be used as a primer and topcoat in one.

- Excellent adhesion to various metals.
- Suitable for a wide range of industrial structures.
- Exterior coating.
- UV resistant.
- Anti-corrosive coating.
- Resistant against wide range of chemicals.
- Direct-to-metal application

TECHNICAL DATA

Binder Type	:	Acrylic
Drying Time	Surface Dry	: <1 hour (at 23°C and 50% humidity)
	Hard Dry	: <3 hours (at 23°C and 50% humidity)
Drying Process	:	Solvent evaporation
Overcoating	:	>4 hours
Viscosity	:	75 - 85KU
Specific Gravity	:	1,30 ±0,025kg/litre
Mass Non-Volatile Content	:	53% ±3%
Fineness of Grind	:	<10 microns
Volume Solids	:	38% ±3%
Coverage	:	6 - 8m ² /litre
Dry Film Thickness	:	54 microns @ 7m ² /litre
Thin & Clean Equipment With	:	Spraying Enamel Thinners, Urethane Thinners
Pack Sizes	:	5 litre, 20 litre

Coverage/spreading rate of **Flexi Coat** depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

APPLICATION

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications. Copies of these are available on request from Dekro Paints or can be downloaded from our website –www.dekro.co.za.

Do not apply when ambient temperatures are <4°C or >40°C.

After correct surface preparation, stir thoroughly and apply a minimum of 2 coats of **Flexi Coat** by brush, roller or spray at the specified spread rate.

Allow to dry between coats as per technical data.



FLEXI COAT

Page 2 of 2

SAFETY INSTRUCTIONS

Always keep out of reach of children and animals.

Wear a suitable dust mask and goggles when preparing surfaces.

Ensure good ventilation during application and drying.

If accidental contact with skin, wash immediately with soap and water or a recognised skin cleaner.

If accidental contact with eyes, rinse immediately with plenty of water and seek medical advice.

Harmful if swallowed. Seek medical attention and do not induce vomiting.

GENERAL

Different surfaces and environmental conditions require specific painting systems to produce the best possible results.

It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

PREVENTING PROBLEMS AND GENERAL INFORMATION

IMPORTANT: Walls (cement plaster, concrete or masonry) must be dry before painting and should not exceed a moisture content of 10% as measured with a Protimeter Surveymaster Moisture Meter or equal.

The ambient temperature must be between 4°C and 40°C and humidity between 10% and 85%.

Excessive application thickness and/or rapid drying could lead to mud cracking.

Avoid applying under adverse weather conditions as this could result in poor product performance.

Do not attempt touch ups, but redo complete panels.

Excessively friable surfaces should be cleaned down prior to primer application.

To ensure consistent appearance ensure that the batch numbers on all containers used are the same.

Where batch numbers on containers differ, intermix containers before use.

CLEANING, STORAGE AND DISPOSAL

Remove as much paint as possible from application equipment and wash immediately after use with water.

Close containers tightly after use and store in a cool well-ventilated area.

Do not empty contents or wash into drains or water courses.

When disposing please follow local authorities' regulations and recycle the container after use.

Avoid storing in direct sunlight and heat.



DEKRO
IS THE ARCHITECTS CHOICE

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.

e-mail: info@dekro.co.za

Toll Free: 0800 222 423

<http://www.dekro.co.za>

